

Aegis® H55WCX Nylon Compound

Description

Aegis® H55WCX is a medium viscosity, heat stabilized, nylon 6 universal wire jacket compound providing excellent performance across the range of THHN, THWN and TFFN constructions. It also offers a well-balanced set of properties including flexibility, toughness, abrasion resistance and excellent resistance to gasoline, oil and other hydrocarbons. Aegis® H55WCX nylon compound has been investigated in accordance with the test methods outlined in ANSI/UL 1581 and ANSI/UL 83 and is certified under UL QMTT2 for use in wire, cable and flexible lighting products.

Typical Properties	ASTM (ISO) Test Method	Dry	Conditioned*
Physical Properties			
Density, g/cm ³	D-792	1.15	
Rockwell Hardness, R Scale	ASTM D-785-08A	116	80
Mechanical Properties			
Tensile Strength, Yield, psi @ 23°C (73°F)	D-638-10	9,300	4,480
Elongation, Yield, % @ 23°C (73°F)	D-638-10	4.6	34
Elongation, Break, % @ 23°C (73°F)	D-638-10	180	360
Flexural Modulus, psi	D-790-10A		
-40°C (-40°F)		521,000	601,000
23°C (73°F)		291,000	82,800
121°C (250°F)		42,100	39,000
Flexural Stress at 5% Strain, psi	D-790-10A		
-40°C (-40°F)		22,500	21,300
23°C (73°F)		10,600	3,420
121°C (250°F)		1,900	1,680
Impact			
Notched Izod Impact, ft-lbs/in	D-256-10A		
-40°C (-40°F)		0.8	0.7
23°C (73°F)		0.9	23
Electrical			
Volume Resistivity, 3.2 mm, Ω·cm	D-257-07	2.19E14	3.63E10
Dielectric Strength, Short Time, 3.2 mm, V/mil	D-149-09	378	235

*Conditioned to 2.7% H₂O (equivalent 23°C [73°F] 50% RH)

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

Page 1 of 2

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

Processing Guidelines

Material Handling

Maximum Water Content: 0.12%

Aegis® H55WCX nylon compound is supplied in sealed containers and drying prior to processing is not required. However, high moisture is the primary cause of processing issues. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 70°C (158°F) is recommended. Drying time is dependent on moisture level. More information about safe handling procedures can be obtained by requesting the Safety Data Sheet on AdvanSix.com.

Melt Viscosity vs Temperature

Melting point, ASTM D-738: 220°C (428°F). The recommended melt temperature range is 240-275°C (464-527°F).

Typical Extrusion Temperature Profile

Barrel: 249-266°C (480-510°F)

Adapter: 260-266°C (500-510°F)

Die: 260-266°C (500-510°F)

Process Melt Temperature: 260-270°C (500-518°F)

Screw Parameters

Metering Section: 40%

Transition Section: 3 to 4 flights

Feed Section: Balance of screw length

Compression Ratio: 3.5:1 to 4.0:1

L/D Ratio: 24:1

Metering Section Flight Depth

Screw Diameter	Recommended Depth
1"	0.055"
1.5"	0.060"
2"	0.070"
2.5"	0.080"
3.5"	0.100"
4.5"	0.115"
6"	0.135"

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

Page 2 of 2

Contact AdvanSix

To learn more about the benefits of Aegis® Nylon Resins, visit

AdvanSix.com/NylonSolutions or call:

1-844-890-8949 (toll free, U.S./Can.)

+1-973-526-1800 (international)

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

AdvanSix

300 Kimball Drive, Suite 101
Parsippany, NJ 07054



Aegis® is a registered trademark of AdvanSix Inc.
September 2020-8, Printed in U.S.A.
©2020 AdvanSix Inc. All rights reserved.

ADVANSIX