

# Aegis® H85WC01 Nylon Compound

## Description

**Aegis® H85WC01** is a medium viscosity, heat stabilized, nylon 6 wire jacket compound providing excellent performance across the range of THHN, THWN and TFFN constructions. It also offers a well-balanced set of properties including low fuming, high toughness, abrasion resistance and excellent resistance to gasoline, oil and other hydrocarbons. Aegis® H85WC01 nylon compound is certified under UL QMTT2 and UL QMTM2 for use in wire, cable, flexible lighting and plenum applications.

Typical Properties	Test Method	Unit	Value
<b>Physical Properties</b>			
Melting Point	ASTM D-3418	°C (°F)	220 (428)
Density	ASTM D-1505	g/cm <sup>3</sup>	1.13
Form	–	–	Pellets
<b>Mechanical Properties (DAM*, 23°C/73.4°F)</b>			
Tensile Strength at Break	ASTM D-638	PSI (MPa)	11,589 (79.9)
Percent Elongation at Break	ASTM D-638	%	48.5
Flexural Strength	ASTM D-790	PSI (MPa)	16,327 (113)
Flexural Modulus	ASTM D-790	PSI (MPa)	419,022 (2,889)
Notched Izod Impact Strength	ASTM D-256	ft-lbs/in (J/m)	0.97 (51.5)

\*DAM = Dry as molded

## Processing Guidelines

### Material Handling

This product is supplied in sealed containers and drying prior to processing is not required. However, higher moisture is the primary cause of processing issues. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 70°C (158°F) is recommended. Drying time is dependent on moisture level. More information about safe handling procedures can be obtained by requesting the Safety Data Sheet on [AdvanSix.com](http://AdvanSix.com).

### Typical Extrusion Temperature Profile

Barrel: 249-266°C (480-510°F)

Adapter: 260-266°C (500-510°F)

Die: 260-266°C (500-510°F)

Process Melt Temperature: 260-270°C (500-518°F)

*The values presented in this data sheet are typical values and are not to be interpreted as product specifications.*

### Contact AdvanSix

To learn more about the benefits of Aegis® Nylon Resins, visit [AdvanSix.com/NylonSolutions](http://AdvanSix.com/NylonSolutions) or call: **1-844-890-8949** (toll free, U.S./Can.) **+1-973-526-1800** (international)

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

**AdvanSix**  
300 Kimball Drive, Suite 101  
Parsippany, NJ 07054



Aegis® is a registered trademark of AdvanSix Inc.  
September 2020-7, Printed in U.S.A.  
©2020 AdvanSix Inc. All rights reserved.