

OxyShield[®] OEB 1500 (2ST) Biaxially Oriented Nylon 6 Film

Description

OxyShield® OEB 1500 (2ST) is a 0.59 mil (15 micron) biaxially oriented nylon 6 film with corona treatment on both sides of the reel. EVOH is incorporated in the core layer to provide extra barrier to oxygen. OxyShield® OEB 1500 (2ST) features a superior balance of properties, including very high barrier to both oxygen and aromas, excellent toughness and puncture resistance under both high and low temperatures, exceptional flex crack resistance and optics. OxyShield® OEB 1500 (2ST) is particularly recommended for packaging requiring very high oxygen barrier OTR <2 cc/m²/24 hours, such as dairy products and meats in modified atmosphere packages.

| Properties | | Typical Value | | T |
|---|--------------|------------------------|------------------|-----------------|
| | | English | Metric | Test Method |
| Average Thickness | Target | 0.59 mil | 15 micron | AdvanSix Method |
| Basis Weight | | 10.74 lbs/ream | 17.5 g/m² | AdvanSix Method |
| Yield | | 40,400 sq. in/lb | 57.5 m²/kg | AdvanSix Method |
| Tensile Strength @ Break | MD | 34,800 psi | 240 MPa | ASTM D-882 |
| | TD | 40,600 psi | 280 MPa | |
| Elongation @ Break | MD | 130% | | ASTM D-882 |
| | TD | 100% | | |
| Elastic Modulus | MD | 424,000 psi | 2,920 MPa | ASTM D-882 |
| | TD | 355,000 psi | 2,450 MPa | |
| Dimensional Stability | MD | 1.5% | | |
| | TD | 1.5% | | |
| Наге | | 3.0% | | ASTM D-1003 |
| Surface Tension | Treated Side | 58 dynes/cm | | ASTM D-2578 |
| Coefficient of Friction, Kinetic | In/In | 0.40 | | ASTM D-1894 |
| | Out/Out | 0.45 | | |
| Oxygen Transmission Rate @ 71.6°F/0% RH, 22°C/0% RH | | 0.08 cc/100 in².day | 1.2 cc/m².day | ASTM D-3985 |

The properties presented in this data sheet are typical values and are not to be interpreted as product specifications.

Contact AdvanSix

To learn more about the benefits of OxyShield[®] films, visit AdvanSix.com or call: 1-844-890-8949 (toll free, U.S./Can.) +1-973-526-1800 (international) Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infrigment, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.



OxyShield® is a registered trademark of AdvanSix Inc. May 2020-4, Printed in U.S.A. ©2020 AdanSix Inc. All rights reserved.



AdvanSix 300 Kimball Drive, Suite 101 Parsippany, NJ 07054