



H.B. Fuller® MM-8805X

Type of Product Hot melt adhesive.

Product Benefits

- high performance
- very fast setting
- very good heat resistance

Typical Applications Packaging, Paper Converting.

Suitable Substrates Paper and Paperboard.

Typical Properties

| Property | Value |
|--------------------|-----------|
| Color | white |
| Softening point | 230°F |
| Viscosity at 350°F | 1 800 cPs |
| Shelf life | 730 days |



| | |
|---------------------------------|---|
| Application Instructions | Application temperature: 350°F |
| Cleaning Instructions | Please contact your local Sales Office for available cleaning solutions. |
| Typical Packaging | Please contact your local Sales Office for available packaging options. |
| Storage Conditions | Clean and dry conditions below 140°F. |
| Disposal Advice | Please refer to the SDS for disposal instructions. |
| Safety Advice | <p>To minimize the risk of burns, we recommend the use of eye protection and protective clothing when working near a hot melt applicator. To minimize the risk of flammable vapors, do not exceed a melt temperature above 400°F. Prevent the build-up of vapors. Extinguish all sources of ignition during hot melt use.</p> <p>Please refer to the MSDS for additional safety advice.</p> |

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is user's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the user's intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: *by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.*



H.B. Fuller

North America
+888-HBFULLER
+888-423-8553
inquiry@hbfuller.com
www.hbfuller.com