

Lunatack[®] AS 301-52

Hotmelt Adhesive

USE Lunatack[®] AS 301-52 has been developed for the manufacture of air filters as pleat separator.

SPECIFICATIONS	Colour	white
	Viscosity¹	10400 mPa*s (150°C)
	Softening point²	ca. 113 °C
	Density	ca. 1.09 g/cm ³
	Approvals	upon request

DELIVERY FORM Blocks

SHELF LIFE In original sealed packaging, at ambient temperature, protected from sun, dust and moisture, at least 12 months.

HEALTH & SAFETY REGULATIONS See material safety data sheet or label.

APPLICATION TYPE Nozzle

WORK INSTRUCTION The application temperature should be between 130 and 150°C depending on the application system.

¹Brookfield DV II+, Spindle 27, ASTM D 3236

²Ring + Ball Softening Point, ASTM E 28-99

IMPORTANT: The information, products, specifications, procedures and recommendations herein (together "information") are based on our experience, and we believe to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is the purchasers sole responsibility to test and determine the suitability of any information for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

H.B. FULLER - EUROPE

H.B. Fuller Austria GesmbH

Phone: (43) (0) 7242 409 0
Fax: (43) (0) 7242 47296

H.B. Fuller Benelux B. V.

Phone: (31) (0) 318 566 000
Fax: (31) (0) 318 566 025

H.B. Fuller Italien S.r.l.

Phone: (39) (0) 321 888 - 800
Fax: (39) (0) 321 888 - 802

H.B. Fuller Europe GmbH

Phone: (41) (0) 1 315 77 00
Fax: (41) (0) 1 312 66 31

H.B. Fuller España S.A.

Phone: (34) (0) 96 514 - 5215
Fax: (34) (0) 96 521 - 6060

H.B. Fuller Deutschland GmbH, Lbg

Phone: (49) (0) 4131 705 - 0
Fax: (49) (0) 4131 705 - 227

H.B. Fuller Deutschland Sp. z o.o.

Phone: (48) (0) 22 82 22 719
Fax: (48) (0) 22 668 54 65

H.B. Fuller Deutschland GmbH, Ni

Phone: (49) (0) 5021 88 - 0
Fax: (49) (0) 5021 88 - 224

H.B. Fuller France SAS

Phone: 0800-917537
Fax: 00800- 8882 8882

H.B. Fuller U.K. LTD

Phone: (44) (0) 161 666 0 666
Fax: (44) (0) 161 666 0 667

H.B. Fuller Sverige AB

Phone: (46) (0) 31 49 66 40
Fax: (46) (0) 31 49 13 26