



## FH8626

### Epoxy Adhesive

#### Product Description

FH8626 is a one-component, low temperature curing epoxy adhesive. This material features fast cure at low temperature, low shrinkage, high adhesive strength, and adhesion to a variety of substrates.

#### Features & Benefits

- One component; no mixing required
- Fast cure at 75°C
- Low modulus to prevent warpage
- Non-conductive; non-corrosive
- Halogen free; REACH and Rohs compliant
- High and low temperature resistance
- Fungus-resistance (does not support growth)

#### Cure Schedule

Cure schedule:

3-5 minutes at 80°C  
15 minutes at 75°C

FH8626 will cure faster with increased temperature. The curing temperature and curing time should be adjusted according to the heating device and the material to be bonded.

Please contact an HB Fuller representative for additional curing recommendations and process parameters.

#### Storage and Handling

FH8626 should be stored at -18°C. Shelf life is a 6 months from date of manufacture, in original unopened containers.

#### Typical Uncured Properties

Property	Value
Chemistry	Epoxy
Color	White
Specific Gravity	1.19
Viscosity at 25°C (cPs)	11910
TI Value	4.1
Work life at 25°C / <60% RH	9 Days

#### Typical Physical Properties of Cured Material (material cured 20 minutes at 80°C)

Property	Value
Hardness, Shore D	82
Elongation at break (%)	1.8
Shear Strength (MPa)	23
Glass transition, Tg (°C)	38.7
Coefficient of thermal expansion (ppm/°C)	$\alpha 1 = 71$ $\alpha 2 = 212.9$
Water absorption after 24hrs at 25°C (%)	0.12

#### Typical Electrical Properties of Cured Material

Property	Value
Dielectric Strength (kV/mm)	27.3
Dielectric Loss	
1KHZ	3.1/0.02
100KHZ	3.2/0.03
Volume resistivity (ohm-cm)	$5.6 \times 10^{15}$
Surface resistivity (ohm)	$1.9 \times 10^{16}$

### Our Focus is Clear. Perfecting Adhesives.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

North America  
+888-HBFULLER  
+888-423-8553

inquiry@hbfuller.com  
www.hbfuller.com



# H.B. Fuller



---

### Directions for use:

---

1. Prior to bonding, surfaces must be free of any dust, oils, or other contaminants.
2. Bring material to room temperature (25°C) before using (typical thaw time for 50mL syringes is 2-4 hours). We do not recommend thawing the material more than 3 times.
3. FH8626 is sensitive to humidity; do not expose the material to air for an extended period of time. The recommended relative humidity during dispensing is <60%.
4. If the material is left idle in the syringe tip for an extended period of time, the tip should be purged or solvent cleaned.
5. Seal any remaining material and store immediately at -18°C.

---

### Clean-Up

---

Equipment and any spillage can be cleaned promptly after use with a mixture of anhydrous isopropyl alcohol and acetone that should be discarded after each use.

---

### Health & Safety Precautions

---

Please see the Material Safety Data Sheet (MSDS) for proper handling and disposal instructions.

## Our Focus is Clear. Perfecting Adhesives.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

North America  
+888-HBFULLER  
+888-423-8553

[inquiry@hbfuller.com](mailto:inquiry@hbfuller.com)  
[www.hbfuller.com](http://www.hbfuller.com)



# H.B. Fuller