



22TL

22TL is a thixotropic anaerobic compounds formulated to cure rapidly and reliably on most "as received" fasteners. They give predictable lubricity on assembly.

Technology / Base	Polyacrylate	
Type of Product	Threadlocking Adhesive and Sealant	
Components	One Component	
Curing	Anaerobic with Secondary Heat Cure	
Appearance / Color	Purple	
Consistency	Thixotropic Liquid	

Features and Benefits

- 100% Solids
- Bolt Threating Range from #2 to 1/2 inch (2.2 to 12 mm)
- MIL (S-46163-A) Type II Grade M

Technical Data			
Physical Property	Value	Condition/Method	
Uncured Material Characteristics			
Viscosity	1200 cPs	Brookfield at 25°C	
Specific Gravity	1.05		
Flash Point	> 93°C		
Shelf Life	12 months unopened		
Storage Condition	8 to 28°C		
Handling Strength	10 to 30 minutes		
Full Cure Conditions	6 to 72 hours at 25°C		
Cured Material Properties			
Pin/Collar Shear Strength	4.1 MPa	ISO 10123	
Service Temperature	-55°C to 175°C		

Technical Data Sheet



H.B. Fuller | Engineering Adhesives



General Instructions

Surfaces to be bonded should be clean and dry and free of grease. Product should be applied in enough quantity to fill all engaged threads or gap. The product performs best in thin bond gaps. Very large gaps may create gaps that will affect the cure speed and overall strength. Good contact is essential. This product is not recommended for use in pure oxygen environments and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. It is recommended to confirm compatibility of the product with all substrates prior to use.

Specifications

MIL (S-46163-A) Type II Grade M ASTM D-5363 AN 0311

Curing Performance

The rate of cure will depend on environmental conditions and the substrates used. The gap of the bond line will affect set speed. Smaller gaps tend to increase set speed. Activators may be applied to further improve set speed, but may also impair overall adhesive performance.

Storage

Products should be stored unopened in a cool, dry place out of direct sunlight. Products may be refrigerated for improved shelf life, but should be brought back to room temperature before use.

Safety and Disposal

For complete safety and handling information, please refer to the appropriate Safety Data Sheets prior to using this product.

> H.B. Fuller Company 9001 W. Fey Drive Frankfort, IL 60423 +1.800.552.0306

www.hbfuller.com

www.hbfullerengineering.com

Connecting what matters.™

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.



® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.

H.B. Fuller www.hbfuller.com