



AT-2 Very High Bond Strength Acrylic Tape

AT-2 is a pressure sensitive, gray, foam core acrylic tape system designed to provide a superior bond between a wide variety of substrates. The tape possesses a uniform, high-tack, acrylic adhesive on both surfaces and will bond to most clean, dry, oil-free substrates.

Thickness ranges from 0.64mm to 1.5mm (0.025" to 0.060")

Width ranges from 6mm to 457mm (0.25" to 18")

Technology / Base	Acrylic
Type of Product	Very High Bond Acrylic Tape
Appearance / Color	Gray
Consistency	Tape

Features and Benefits

AT-2 offers numerous advantages including increased compressibility, a waterproof bond, ease of application, and the ability to withstand thermal movement.

- Pressure sensitive bonding
- Compressible with foamed core
- Moisture resistant
- Excellent weathering properties
- Maintains adhesion at sub-zero temperatures
- Hardening or brittle resistant with age
- Flexible – conforms to intricate shapes

Technical Data

Property	Typical Value	Test Method
Tensile Strength (kPa)	960	ASTM D412 Die C
Elongation (%)	900	ASTM D412 Die C
Dynamic Shear(kPa)	415	ASTM D3163
Static Shear	Passes @ 74°F Passes @158°F	WSB-M3G138-B (1000g, 1 in ² , 100hrs)
90° Peel Adhesion (N/mm)	4	ASTM D3330
UV Resistance	Maintains minimum 90% of initial strength	2 weeks UV-A @ 140°F
Application Temperature Range	10°C to 38°C (50°F to 100°F)	
Service Temperature Range	-34°C to 93°C (-30°F to 200°F)	



Typical Applications

- Automotive trim attachment
- Signs
- Graphics
- Window muntin bar attachment
- Furniture
- Appliances
- Many other manufacturing and construction applications to replace mechanical fasteners and welds

Specifications

Typical Packaging

Contact your H.B. Fuller representative for specific sizes.

Storage and Shelf Life

Store material in original unopened packaging at temperatures between 4°C to 38°C (40°F to 100°F). Shelf life is 24 months when stored as recommended.

Safety and Disposal

Prior to working with this or any product consult product label and Safety Data Sheet (SDS) for necessary health and safety precautions and disposal considerations.

General Instructions

1. Substrate Evaluation: Acrylic adhesive is suitable for bonding a variety of substrates, including many plastic composites, sealed wood, and metals. Low surface energy materials such as polyethylene, polypropylene, silicones and PTFE can be difficult to bond to. Thorough evaluation is recommended when bonding to any questionable surface. An adhesion promoter (primer) for use with pressure sensitive acrylic adhesives may be necessary to facilitate proper bonding, and is available from H.B. Fuller.
2. Preparation of Substrate: The substrate to be bonded should be cleaned with an appropriate solvent, preferably isopropanol (IPA). The acrylic adhesive backed part should be applied within 15 minutes of cleaning. To ensure removal of all contaminants without leaving any residue, use a clean, lint-free wiping cloth or disposable wipe. Never use recycled rags. Other solvents such as hexane, heptane, or methanol may be suitable for cleaning various substrates after thorough evaluation. The substrate must be completely dry through evaporation of the solvent with radiant heat, hot air dryers, or with time before bonding acrylic adhesive backed parts.
3. Adhesive Promoter Application-If necessary: Apply the AP-1 Adhesion Promoter to the substrate(s) either with a lint-free applicator or foam brush. Apply the Adhesion Promoter in a "wet" laydown thickness range of 1-8 mils. Allow the Adhesion Promoter to dry approximately 5 minutes. Don't touch the Adhesion Promoter.
4. Application of Adhesive Backed Part to the Substrate: Remove the protective release liner from the acrylic tape immediately prior to applying the part to be bonded, being careful not to contaminate the acrylic adhesive. Apply within 15 minutes after surface preparation. Apply the part to be bonded without entrapping air between the tape and the substrate with a recommended minimum application pressure of 15 pounds per inch of tape width to achieve adhesive to substrate contact and maximum bond

H.B. Fuller Company
 4401 Page Ave
 Michigan Center, MI 49254
 Tel: +1.800.248.4011

Connecting what matters.™

www.hbfuller.com

www.hbfullerengineering.com

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.



NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

H.B. Fuller
www.hbfuller.com

©H.B. Fuller Company, 2020