

RP100

RP100 is a medium viscosity, rapid curing, cyanoacrylate adhesive for general purpose bonding. It is designed to bond a wide range of similar and dissimilar materials. Handling strength in most applications is in 10 seconds.

Technology / Base	Ethyl		
Type of Product	Cyanoacrylate		
Components	One Component		
Curing	Humidity		
Appearance / Color	Clear		
Consistency	Liquid		

Technical Data				
Uncured Material Characteristics		Value	Condition/Method	
Viscosity		100 cPs		
Specific Gravity		1.05		
Storage Condition		< 22°C		
Set Time	Steel	< 20 sec		
	Aluminum	<15 sec		
	Neoprene	<5 sec		
	ABS	<10 sec		
	PVC	<5 sec		
	Polycarbonate	<30 sec		
	Phenolic	<10 sec		
Cured Material Characteristics				
Shear Strength	Steel	>2100 psi	ISO 4587	
	Aluminum	>1750 psi	ISO 4587	
	Neoprene	>750 psi	ISO 4587	
	ABS	>900 psi	ISO 4587	
	PVC	>900 psi	ISO 4587	
	Polycarbonate	>900 psi	ISO 4587	
	Phenolic	>850 psi	ISO 4587	
Tensile Strength		>1800 psi	ISO 6922	
Damp Heat Aging		100%	Strength on PC after 500 hrs at 40°C,	
			95% R.H.	
Dielectric Constant		2 to 3.5 at 1kHz	ASTM D150	
Dissipation Factor		< 0.02 at 1kHz	ASTM D150	
Volume Resistivity		2 to 10 x 10^15 ohm cm	ASTM D257	



General Instructions

For optimum results parts should be clean and free from any contamination on the bonding surface. If parts do not mate flush together use a higher viscosity product to compensate for the gap. Factors Affecting Cure Speed Include: GAP: Thin bond line results in faster cure speed. Larger gaps will lengthen cure speed. HUMIDITY: Cure and fixture times can be influenced by the humidity conditions at the time of assembly. The higher the RH the faster cure and fixture times will be. Fixture time data based on our testing is conducted at 50% relative humidity.

Specifications and Approvals

Mil Spec 46050 C Type II Class 2

Storage

Store product in unopened containers, out of direct sunlight, in a dry location. Material should be stored at or below 22°C. For extended shelf life unopened containers of the product may be refrigerated.

Safety & Disposal

For safe handling information and disposal instructions on this product, consult the Safety Data Sheet (SDS)

Date Modified: 01 December 2010

H.B. Fuller Company 9001 W. Fey Drive Frankfort, IL 60423 +1.800.552.0299

www.hbfuller.com

Connecting what matters.™

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply



H.B. Fuller www.hbfuller.com

©H.B. Fuller Company, 2020