Technical Information POLYCAT® 41

Description

POLYCAT[®] 41 is a tertiary amine catalyst used in a wide variety of polyurethane foam and non-foam applications.

Key performance benefits

- Improved curing of PUR systems
- Delayed front end activity as PIR co-catalyst

Typical properties*	
Appearance	Clear liquid
Viscosity at 25 °C	33 mPa·s
Density at 25 °C	0.91 g/cm ³
Calculated OH number**	n.a.

* For actual ranges, please refer to the Certificate of Analysis (CoA) / Sales Specification. | ** n.a. = not applicable

Application

POLYCAT® 41 is a gel catalyst with additional mild PIR selectivity used in a wide variety of rigid polyurethane and polyisocyanurate foam and nonfoam applications. It is recommended for use as a co-catalyst with other polyurethane and polyisocyanurate catalysts, particularly in formulations with an isocyanate index greater than 105 – 110.

POLYCAT[®] 41 has a certain hydrolysis sensitivity. Hence stability testing of formulations containing POLYCAT[®] 41 is highly recommended. POLYCAT[®] 41 may be used in conjunction with suitable co-catalysts from the DABCO[®], POLYCAT[®] and/or KOSMOS[®] range, based on specific formulation requirements.

In PIR formulations, POLYCAT® 41 can be used as co-catalyst in conjunction with trimerization catalysts such as products of the KOSMOS® and DABCO® TMR series.

POLYCAT® 41 and potassium/metal catalyst should not be pre-blended as it might lead to incompatibilities. Separate dosing and/or blending into the polyol is preferred.

Common use levels of POLYCAT® 41 are in the range of 0.5 and 3.0 parts per 100 parts of polyol. The optimal concentration will depend on specifics of the formulation.

Storage recommendations

- Shelf life: minimum 12 months. For exact date of expiration, please consider CoA.
- Storage conditions: dry and cool place in factory-packed containers.
- Optimum storage temperature: 10 to 30 °C.

Safety instructions

Please consult the Safety Data Sheet for summary of product hazards, personal protective measures, and emergency release procedures.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice. Evonik Operations CmbH Rellinghauser Straße 1–11 45128 Essen, Germany Phone: +49 201 173 3006 Email: polyurethane@evonik.com



For any further information, contact either your regional sales or technical support or visit our customer portal <u>explorepu.evonik.com</u>.

