



Polypropylene: **INSPIRE 6123EN**

Sub-group
Random Copolymer

Description
High performance nucleated polypropylene with great balance of clarity and physical properties

Applications
Suggested uses include extrusion and thermoforming processes, especially suited for applications requiring excellent clarity

Control Properties	ASTM Method	Units	Values
Nominal Melt Flow (230°C/2.16kg)	D-1238	g/10 min	2.0

Typical Properties	ASTM Method	Units	Values
Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant)	D-790A	psi(MPa)	190,000(1,310)
Notched Izod Impact Strength at 23°C	D-256A	ft-lb/in(J/m)	1.0(53)
Heat Deflection Temperature 66 psi (0.45 Mpa)	D-648	°C (°F)	100(212)

Final Remarks

1. For food contact information, including U.S. Food and Drug Administration (FDA) compliance, please refer to the Regulatory Information Sheet (RIS) available at www.braskem.com.
2. Read Safety Data Sheet before use.
3. This information reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
4. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
5. In case of doubt regarding utilization, or for other applications, please contact Technical Service.
6. The values in this report can be modified without prior communication from Braskem.
7. For Product Stewardship Information, please contact Braskem at us_compliance@braskem.com.

Revision

Date: 7/21/2020
www.braskem.com