

High Density Polyethylene GE7252XP

Description:

GE7252XP is a bimodal high density polyethylene developed for the manufacturing of caps and closures for beverages with low or mild carbonation levels. This grade offers a good balance between chemical and mechanical resistance and good processability.

Additivation:

Slip agent

Applications:

Caps for non-carbonated or low carbonated soft drinks, Caps for water

Processes:

Compression Molding, Injection molding.

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	2.0
Density	D 792	g/cm ³	0.952

Typical Properties - Plaque¹:

Plaque Properties

Feature	Method	Units	Values
Tensile Strength at Yield (a)	D 638	MPa	27
Tensile Strength at Break (a)	D 638	MPa	36
Flexural Modulus - 1% Secant (b)	D 2240	MPa	1110
Shore D Hardness (c)	D 1693	-	62
Izod Impact Strength (b)	D 256	J/m	65
Environmental Stress Cracking Resistance - notch 0,3 mm; 50°C; 10% Igepal CO630 (a)	D 1693	h/F50	35
Environmental Stress Cracking Resistance - notch 0,3 mm; 50°C; 100% Igepal CO630 (a)	D 1693	h/F50	65
Deflection Temperature under Load at 0.455 MPa (b)	D 648	°C	65
Vicat Softening Temperature at 10 N (b)	D 1525	°C	126

¹ Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break.

Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.