

Unilene B-110

Description:

Thermoplastic hydrocarbon resin C9 is obtained from catalytic polymerization of hydrocarbons in a continuous process. Compatible with most solvents and polymeric materials, it has hydrophobic characteristics and has a format of light yellow pellets.

In rubbers, Unilene improves processability, filler incorporation, dispersion and mass adhesion, avoiding elastomer degradation and reducing preparation time. In Solvent and Hot Melt adhesives, the resin promotes good adhesion, cohesion, excellent open time and water repellency.

Applications:

Hot melt adhesives (EVA, metallocene PE and PSA) and solvent based , In addition, the product can be used for seals and sealants, paints and varnishes (road marking, printing inks, aluminum and protective, epoxy and alkyd systems), tires and rubber artifacts and polymer modification.

Typical Values

Feature	Method	Units	Values
Softening Point	ASTM D 6493	°C	110
Gardner Color	ASTM D 6166	-	6 max.
Acid Value	ASTM D 974	mg KOH/g	0,1 máx.
Molecular Weight (Mn)	ASTM D 6579	g/mol	740
Molecular Weight (Mw)	ASTM D 6579	g/mol	1530
Molecular Weight (Mz)	ASTM D 6579	g/mol	2900
Viscosity Brookfield (@180°C)	ASTM D 3236	cP	320
Cloud Point (MMAp)	ASTM D 6038	°C	29
Glass Transition Temperature	ASTM D 6604	°C	63

Packaging and Storage:

The resins are supplied in 25 ± 0.2 kg polyethylene bags and are supplied in pellet format. Hydrocarbon resins have thermoplastic characteristics, they can agglomerate when submitted to high temperatures and / or under pressure (stacking). It is recommended to store the product in fresh place, free from direct sunlight, moisture and without stacking the pallets, also avoiding direct contact with the soil.

This characteristic is considered more critical for low softening point resins such as Unilene A-80, A-90 and A-90 LN.

Expiration date:

Two years from production date. Please refer to storage conditions recommendations.

Legal Statement

- For safety, handling, personal protection, first aid and waste disposal information, refer to the SDS - Safety Data Sheet.
- For any doubt concerning material handling or application, please contact the Technical Services area.
- The properties and values contained in the quality certificate must be considered as a guarantee of the product. For typical values, when provided, the information is given in good faith and obtained in our laboratories, and should not be considered as absolute or as a guarantee.
- This document may not be distributed, displayed, copied or altered without prior written permission of Braskem SA. To the extent Braskem SA authorizes the distribution, display, and / or copying of this document, you may do so only if the document is unaltered and complete, including all headers, footers, disclaimers, and other information.