

High Density Polyethylene SGF4960

Description:

SGF4960 is a homopolymer high-density polyethylene, developed for the blow-molding segment with high density and stiffness combined with high impact resistance. The minimum biobased carbon content of this grade is 96%, determined according to ASTM D6866.

Aplicações:

Blow molding small volumes, Dairy based products packaging, Juice packaging, Food packaging, bottles for ethylic alcohol, toys

Processos:

Extrusion Blow Molding

Control Properties:

Característica	Método	Unidades	Valores
Density	ISO 1183-1	g/cm ³	0.962
Melt Flow Rate (190°C/2,16 kg)	ISO 1133	g/10 min	0.34

Typical Properties - Plaque¹:

Plaque Properties

Característica	Método	Unidades	Valores
Tensile Strength at Yield (b)	ISO 527	MPa	30
Tensile Strength at Break (b)	ISO 527	MPa	17
Flexural Modulus Chord 0.05-0.25 % (b)	ISO 178	MPa	1410
Izod Impact Strength 23 °C (b)	ISO 180	kJ/m ²	9
Vicat Softening Temperature at 10 N (a)	ISO 306	°C	128
Deflection Temperature Under Load at 0.455 MPa (b)	ISO 75	°C	70

¹ Test specimens prepared from compression molded sheet made according to ISO 293. Plaque Thickness: a) 3 mm b) 4 mm c) 6 mm

Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.