

## High Density Polyethylene SHA7260

### Description:

SHA7260 is a high-density polyethylene, developed for the injection molding, easy to process and with high productivity. This resin has a good melt flow with high rigidity and hardness. Its narrow molar mass distribution results in a low tendency to warpage. The minimum biobased carbon content of this grade is 94%, determined according to ASTM D6866.

### Aplicações:

Caps, Thin wall parts, Houseware, toys

### Control Properties:

Característica	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	20
Density	D 792	g/cm <sup>3</sup>	0.955

### Typical Properties - Plaque<sup>1</sup>:

Plaque Properties

Característica	Method	Units	Values
Tensile Strength at Break (a)	ASTM D 638	MPa	26
Flexural Modulus - 1% Secant (b)	D 2240	MPa	1250
Hardness (c)	D 2240	-	60
Izod Impact Strength (b)	D 256	J/m	20
Deflection Temperature under Load at 0.455 MPa (b)	D 648	°C	67
Vicat Softening Temperature at 10 N (b)	D 1525	°C	121

<sup>1</sup> Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break.

### Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.