

High Density Polyethylene SHC7260LS-L

Description:

SHC7260LS-L is a high-density polyethylene, developed for the injection molding which presents high hardness and stiffness, besides low tendency to warpage. This resin has additives against the ultraviolet radiation action. The minimum biobased carbon content of this grade is 94%, determined according to ASTM D6866.

Applications:

Pallet, Safety helmet, General use crates, Industrial crates

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	7.2
Density	D 792	g/cm ³	0.959

Typical Properties - Plaque¹:

Plaque Properties

Feature	Method	Units	Values
Tensile Strength at Yield (a)	D 638	MPa	29
Elongation at Yield (a)	D 638	%	7.5
Flexural Modulus - 1% Secant (b)	D 2240	MPa	1375
Shore D Hardness (c)	D 2240	-	63
Izod Impact Strength (b)	D 256	J/m	35
Deflection Temperature under Load at 0.455 MPa (b)	D 648	°C	74
Vicat Softening Temperature at 10 N (b)	D 1525	°C	126

¹ Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break.

Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.