

high Density Polyethylene HDI2061

Description:

HDI2061 is a High Density Polyethylene for Injection Molding Segment. By having good fluidity provides excellent processability, which promotes high productivity combined with good stiffness and hardness. The narrow molecular weight distribution gives low tendency to deformation.

This resin complies with ANSI/NSF Standard 61 and ANSI/NSF Standard 51.

The benefit of having both certifications makes this resin ideal for fittings that require direct contact with food and/or potable water.

Applications:

Medium to thin wall items, toys, large caps, household containers, caps.

Processes:

Injection molding

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	ASTM D1238	g/10 min	20.00
Density	ASTM D792	g/cm ³	0.955

Typical Properties¹

Feature	Method	Units	Values
Tensile Strength at Yield	ASTM D638	MPa	27
Tensile Strength at Break	ASTM D638	MPa	14
Elasticity Modulus (Secant 1%)	ASTM D 638	MPa	1278
Flexural Modulus (Secant 1%)	ASTM D790	MPa	1273
Izod Impact Strength ³	ASTM D 256/A	J/m	32
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	70
Vicat Softening Point (10 N)	ASTM D1525	°C	125
ESCR (100% Igepal) ²	ASTM D 1693	h	3

¹ Test specimens from compression molded plaque according to ASTM D4703.

² Condition B.

³ Test temperature at 23°C.

Final Remarks

- It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
- The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
- Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
- The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
- For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
- The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.