

## Polyisobutene PIB 121

### Description:

PIB 121 is produced by polymerization of an isobutene rich stream with specific catalyst. The product is clear, bright and free from impurities. Among all possible applications, it can be used in lubricants and synthetic oils formulation.

### Applications:

Lubricants

### Typical Values:

Feature	Method	Units	Values
Viscosity (@ 100°C)	ASTM D 445	cSt	3000
Viscosity (@ 40°C)	ASTM D 445	cSt	122000
Viscosity Index	ASTM D 2270	-	250
Water	ASTM D 6304	ppm	40
Flash Point	ASTM D 92	°C	240
Color	ASTM D 1209	Pt-Co	50
Molecular Weight (Mn)	Internal - GPC	Daltons	2200
Polydispersity Index (Mw/Mn)	Internal - GPC	-	3
Pour Point	ASTM D 97	°C	17
Density (20/4°C)	ASTM D 4052	-	0.91
Refractive Index	ASTM D 1218	nD	1.5
Chlorine	ASTM D 5808	ppm	170

#### Packaging and storage:

PIB is supplied in 175 kg metallic drums or in isotanks. Polybutene polymer must be stored at temperatures under 50°C, and protected from direct sunlight, moisture and in order to avoid direct contact with the soil.

#### Shelf life:

3 (three) years from production, since the recommended storage conditions are respected.

### Legal Statement

- For safety, handling, personal protection, first aid and waste disposal information, refer to the SDS - Safety Data Sheet.
- For any doubt concerning material handling or application, please contact the Technical Services area.
- The properties and values contained in the quality certificate must be considered as a guarantee of the product. For typical values, when provided, the information is given in good faith and obtained in our laboratories, and should not be considered as absolute or as a guarantee.
- This document may not be distributed, displayed, copied or altered without prior written permission of Braskem SA. To the extent Braskem SA authorizes the distribution, display, and / or copying of this document, you may do so only if the document is unaltered and complete, including all headers, footers, disclaimers, and other information.