

Polyisobutene PIB 30

Description:

PIB 30 is obtained by polymerization of an isobutene rich stream with specific catalysts. Product is composed predominantly of aliphatic mono-olefins. It is clear, bright and free from sediments or suspended matter.

PIB 30 is a non-toxic polymer and has NSF certification. It can be used in lubricants and synthetic oils formulation, including for food grade and pharmaceutical grade. PIB 30 is also applied in cosmetics as lip-gloss and in formulations of stretch film.



Nonfood Compounds
H1

Applications:

Lubricants, Adhesives, Cosmetics, Stretch Films

Typical Values:

Feature	Method	Units	Values
Viscosity (@ 100°C)	ASTM D 445	cSt	630
Viscosity (@ 37.8°C)	ASTM D 445	cSt	19500
Viscosity Index	ASTM D 2270	-	186
Water	ASTM D 6304	ppm	40
Flash Point	ASTM D 92	°C	190
Color	ASTM D 1209	Pt-Co	50
Molecular Weight (Mn)	Internal - GPC	Daltons	1300
Polydispersity Index (Mw/Mn)	Internal - GPC	-	1.80
Pour Point	ASTM D 97	°C	3
Density (20/4°C)	ASTM D 4052	-	0.90
Acid Number	ASTM D 974	mg KOH/g	0.01
Bromine Number	ASTM D 1159	g Br ₂ /100g	14
Chlorine	ASTM D 5808	ppm	160
Sodium	ASTM D 4951	ppm	< 2

Packaging and storage:

PIB is supplied in 175 kg metallic drums or in isotanks. Polybutene polymer must be stored at temperatures under 50°C, and protected from direct sunlight, moisture and in order to avoid direct contact with the soil.

Shelf life:

3 (three) years from production, since the recommended storage conditions are respected.

Legal Statement

- For safety, handling, personal protection, first aid and waste disposal information, refer to the SDS - Safety Data Sheet.
- For any doubt concerning material handling or application, please contact the Technical Services area.
- The properties and values contained in the quality certificate must be considered as a guarantee of the product. For typical values, when provided, the information is given in good faith and obtained in our laboratories, and should not be considered as absolute or as a guarantee.
- This document may not be distributed, displayed, copied or altered without prior written permission of Braskem SA. To the extent Braskem SA authorizes the distribution, display, and / or copying of this document, you may do so only if the document is unaltered and complete, including all headers, footers, disclaimers, and other information.