

AQUACER 8330

Paraffin-based wax emulsion for aqueous systems.

AQUACER 8330 is only available in USA, Mexico and Canada.

Product Data

Composition

Anionic emulsion of a modified paraffin wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (ASTM D2834): 30 %
Carrier: Water
Melting point (wax component): 60 °C (140 °F)
Viscosity (25 °C, Brookfield DV-I): < 2,000 mPa·s
pH value (ASTM E70): 10

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Keep from freezing. To be stored and transported at a temperature between 5 °C (41 °F) and 35 °C (95 °F). AQUACER 8330 will begin to slowly separate on standing. However, it is easily reconstituted with mild agitation.

Applications

Coatings Industry

Special Features and Benefits

The additive improves water repellency and anti-blocking properties and increases surface slip in aqueous systems.

Recommended Use

AQUACER 8330 can be used in outdoor coatings, in lumber end coatings, in pressboard end sealers and other applications.

Incorporation and Processing Instructions

The additive is preferably incorporated into the coating with a low shear rate at the end of the production process. Stir well before use.

AQUACER 8330

Data Sheet
Issue 06/2015



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABÉN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA