

# BYK-345

Silicone surfactant for aqueous coatings, printing inks and overprint varnishes with strong reduction in surface tension resulting in significantly improved substrate wetting. No increase in surface slip. Solvent-free version of BYK-346.

## Product Data

### Composition

Polyether-modified siloxane

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.04 g/ml

Active substance: 100 %

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Special Note

Solvent-free version of BYK-346. The additive requires a small amount of co-solvent in the formulation (approx. 5 % of the total solvent content) in order to avoid turbidity. The effectivity of the silicone surfactant is reduced in systems with higher co-solvent amounts. For these types of formulations we recommend the use of polysiloxanes such as BYK-333.

## Applications

### Coatings and Printing Inks

#### Special Features and Benefits

The additive provides a large decrease in surface tension in aqueous systems and therefore improves substrate wetting and leveling in particular. Foam stabilization does not occur or only very minimally and recoatability is not affected. The additive does not increase surface slip. If higher surface slip is desired, we recommend combining it with a polysiloxane such as BYK-333.

#### Recommended Use

The additive is recommended for all aqueous coatings, printing inks and overprint varnishes which contain a small proportion of organic co-solvent.



**Recommended Levels**

0.05-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

**Incorporation and Processing Instructions**

The additive is preferably added to the finished formulation. It can, however, be added at any stage during production.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

**info@byk.com**  
**www.byk.com**

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany