

BYK-A 525

Defoamer/air release agent for potting compounds, sealants and adhesives (polyurethane and epoxy). Contains silicone.

Product Data

Composition

Solution of a polyether-modified methylalkyl polysiloxane copolymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 0.86 g/ml

Solvents: White spirit/Methoxypropylacetate 9/1

Flash point: 38 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Adhesives & Sealants

Special Features and Benefits

Prevents foam and bubble formation during manufacturing and application. It demonstrates excellent air release characteristics in mineral-filled systems. It additionally improves wetting of quartz and glass fibers.

Recommended Use

Especially recommended for systems on polyurethane and epoxy resin basis.

Recommended Levels

0.1-0.5 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate into resin before adding the other components.

Ambient Curing Systems

Special Features and Benefits

Acts as a defoamer/air release agent during production and application. Also reduces surface tension, improves leveling and wetting and prevents Bénard cell formation. The decrease in surface tension can be reduced by lowering the polarity of the binder system.

Recommended Use

Especially recommended for systems on polyurethane and epoxy resin basis.

Recommended Levels

0.3-1 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate into resin before adding the other components. Can also be added to complete systems.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany