

Lab Product Data Sheet

BYK-LP N 6322

Stand : 04/2009
Version.

Wetting and Dispersing Additives for Solvent-borne and Solvent-free Systems

Composition

BYK-LP N 6322	Solution of a salt of unsaturated polyamine amides and acidic polyesters
----------------------	--

Typical Properties

Solvent	Hydrocarbons
Density at 68 F	7.21 lbs/US gal
Non volatile matter	52 %
Flashpoint	100 °F
Amine value	19 mg KOH/g
Acid value	26 mg KOH/g

Recommended Levels

% additive (as supplied) based upon

inorganic pigments	titanium dioxide	organic pigments	Bentonites
1 - 2	0.5 - 1	2 - 10	-

Special Hints

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Separation or turbidity may occur during storage and transportation. Mix well before use. Warm to 30-60°C (90-140°F) and mix well.

This additive is a test product and only on request commercially available

Lab Product Data Sheet

BYK-LP N 6322

Stand : 04/2009
Version.

ANTI-TERRA®, ATEPAS®, BYK®, BYK-DYNWET®, BYK-SILCLEAN®, BYKANOL®, BYKJET®, BYKETOL®, BYKO-PLAST®, BYKUMEN®, DISPERBYK®, DISPERPLAST®, ISAROL®, LACTIMON®, NANOBYK®, SCONA®, and VISCOBYK® are registered trademarks of BYK-Chemie.

AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER® and MINERPOL® are registered trademarks of BYK-Cera.

This information is given to the best of our knowledge. Because of the multitude of formulations, production and application conditions, including those for patent rights, can be derived from this fact for individual cases.

Particle size distribution.