

DISPERBYK-199

VOC-free wetting and dispersing additive for aqueous coatings and adhesives as well as pigment concentrates for stabilizing organic and inorganic pigments.

Product Data

Composition

Solution of a copolymer with pigment-affinic groups

VOC-free (< 1500 ppm)
Contains no alkylphenol
ethoxylates.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.11 g/ml
Non-volatile matter (20 min., 150 °C): 40 %
Solvents: Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 0 °C. Warm to 20 °C and mix well.

Applications

Coatings Industry

Special Features and Benefits

DISPERBYK-199 uses electrosteric stabilization to deflocculate the pigments. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding power are also increased and viscosity is reduced. In this way, the flow characteristics are also improved and a higher pigment load is possible. The additive represents an alternative to the polyelectrolyte-based and high molecular weight wetting and dispersing additives that are usually used in aqueous systems and is suitable for both inorganic and organic pigments.

Recommended Use

DISPERBYK-199 is recommended for aqueous coatings (PVC 16-35 %) and highly filled pigment concentrates.

Architectural coatings	<input checked="" type="checkbox"/>
Protective coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input type="checkbox"/>
Leather coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

Amount of additive (as supplied) based on the pigment:

Titanium dioxides:	2.5-7.5 %
Inorganic pigments:	10-30 %
Organic pigments:	37-100 %
Carbon blacks:	75-125 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added to the millbase before the incorporation of the pigments.

Adhesives & Sealants

Special Features and Benefits

DISPERBYK-199 deflocculates fillers and pigments through electrosteric stabilization. In filled adhesive systems, the viscosity is considerably reduced, enabling easier processing or a higher filler loading. It represents an alternative to the polyelectrolyte-based and high molecular weight wetting and dispersing additives that are usually used in aqueous systems and is particularly suitable for inorganic fillers and pigments. DISPERBYK-199 is recommended for all aqueous dispersion adhesives and sealants.

Recommended Levels

Amount of additive (as supplied) based on the pigment:

Titanium dioxides:	1.5-2 %
Inorganic pigments:	2-10 %
Filler:	0.5-1 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive should be added to the system before the incorporation of the fillers and pigments.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany