

DISPERBYK-2012

Wetting and dispersing additive for aqueous coatings and printing inks. Particularly suited for grinds that contain binders (emulsions and water-reducible resins) as well as for binder-free pigment concentrates.

Product Data

Composition

Solution of a copolymer with pigment-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.


Amine value:	7 mg KOH/g
Acid value:	7 mg KOH/g
Density (20 °C):	1.06 g/ml
Non-volatile matter (20 min., 150 °C):	40 %
Solvents:	Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.









Applications

Coatings and Printing Inks

Special Features and Benefits

Due to its broad compatibility with many aqueous binders, DISPERBYK-2012 is the first choice for grinds that contain binders. It stabilizes a multitude of pigments, primarily transparent and opaque organic pigments and carbon blacks. Also for binder-free grinds, it has versatile applications and the presence of amines, rheology additives, wetting agents and organic co-solvents in the millbase is not a problem. This high molecular weight additive improves color strength, transparency, gloss, and storage stability through steric stabilization. It has no influence on the stability of pH-sensitive systems and is therefore particularly recommended for use in formulations based on cationic binders. Furthermore, DISPERBYK-2012 is suitable for use in aqueous road marking paints.

Recommended Use

Automotive coatings	
Industrial coatings	
Wood and furniture coatings	
Architectural coatings	
Leather coatings	
Printing inks	

 especially recommended  recommended

Recommended Levels

Amount of additive (as supplied) based on the pigment:

Inorganic pigments: 5-30 %
 Titanium dioxides: 4-10 %
 Organic pigments: 50-100 %
 Carbon blacks: 100-230 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase. In the case of grinds that contain binders, the resin and water should be pre-mixed and then gradually let the additive flow in while stirring. If the water-soluble binder requires neutralization, the amine should be added prior to the DISPERBYK-2012. In the case of binder-free grinds, simply pre-mix the water and additive. In all cases, only add the pigments when the additive has been thoroughly distributed.



Additive Guide

**BYK-Chemie GmbH**

P.O. Box 10 02 45
 46462 Wesel
 Germany
 Tel +49 281 670-0
 Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany