

HORDAMER PE 02

Polyethylene primary dispersion for formulating release agents for metal die casting. Improves surface protection in aqueous care products and adhesion in dispersion adhesives. Anti-caking additive for thermoplastics and hot-melt adhesives. Wetting and dispersing agent for thermoplastic color masterbatches.

Product Data

Composition

Primary polyethylene dispersion containing an anionic emulsifier

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

| | |
|------------------------------|-----------|
| Density (20 °C): | 0.97 g/ml |
| Non-volatile matter: | 40 % |
| Carrier: | Water |
| Melting point (wax content): | 95 °C |
| Viscosity (20 °C): | 20 mPa·s |
| pH value (20 °C): | 8-12 |

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C and 35 °C. Stir before processing.

Special Note

During storage, the pH value may drop to a value as low as pH 8. This does not impact the performance of the product.

Applications

Release Agents for Metal Die Casting

Special Features and Benefits

HORDAMER PE 02 is recommended for the formulation of aqueous mold release agents that are used in aluminum die casting. The product enables the thorough wetting of the mold at high temperatures, excellent film formation and outstanding adhesion to the mold surface. The mold is protected from damage and the surface quality of the finished moldings is excellent.

Recommended Levels

10-70 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

HORDAMER PE 02 is preferably diluted with water, but may also be mixed directly with all components of the aqueous mold release agent.

Hot-Melt Adhesives

Special Features and Benefits

HORDAMER PE 02 is used as an anti-caking additive in the manufacture of hot-melt adhesives during underwater pelletizing so as to obtain free-flowing and non-sticking granulated material. It is directly added to the cooling water and, therefore, is easy to handle and dust-free.

Recommended Levels

0.5–5 % additive (as supplied) based upon the amount of water in the cooling circuit.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added directly to the circuit water. If foaming occurs in the circuit water, we recommend defoamers BYK-023 (silicone defoamer) or BYK-016 (silicone-free) at a dosage of 0.05-0.3 %.

Packaging Adhesives

Special Features and Benefits

HORDAMER PE 02 improves the adhesive properties of aqueous emulsion adhesives intended for packaging. In the bonding of film laminated surfaces using paper or cardboard, HORDAMER PE 02 improves adhesion on the side facing the film. Adhesion is particularly enhanced on films made of oriented polypropylene (OPP), bi-axially oriented PP (BOPP) and, in some cases, also polyethylene (PE). The product has good adhesion properties also at low temperatures. HORDAMER PE 02 prevents yellowing when storing bonded systems at higher temperatures. HORDAMER PE 02 is a part of the binder in these applications, which is why it is added in greater quantities.

Recommended Levels

10–50 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added after admixture of the binder.

Thermoplastics

Special Features and Benefits

Thermoplastic granulated material (TPE, TPU, EVA) tends to compact and cake under pressure and heat. HORDAMER PE 02 is used in the underwater pelletizing of such materials and forms a protective layer covering the granules, thereby generating non-sticking and free-flowing granulated materials. Unlike the commonly performed dusting of the granulate materials using solid release agents (chalk, talc), significantly lower quantities are needed, which, therefore, avoid an impact on the properties of the thermoplastic material. The generation of dust during processing is also eliminated.

Recommended Levels

0.2–5 % additive (as supplied) based upon the amount of water in the cooling circuit.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added directly to the circuit water. If foaming occurs in the circuit water during the underwater granulation, we recommend defoamers BYK-023 (silicone defoamer) or BYK-016 (silicone-free) at a dosage of 0.05-0.1 %.

Wetting and Dispersing

Special Features and Benefits

HORDAMER PE 02 is a wax dispersion that can improve mixing and compounding in the manufacturing of color masterbatches. This results in better dispersion, better color properties, and a lower filter pressure value.

Premix:

Adding up to 8 % to the premix reduces the formation of dust during processing and helps to limit the free flowing effect of organic pigments during the mixing process, which leads to greater shear forces and a better pre-dispersion.

Extrusion:

During extrusion, the finely dispersed wax particles ensure good wetting and thus prevent compaction. The torque build-up, throughput, viscosity (MVR), filter pressure value (FPV) and dispersion quality are improved.

Recommended Use

HORDAMER PE 02 is suitable for dispersing solids in polyethylene (PE) and polypropylene (PP).

Recommended Levels

Organic pigments: 5-8 % additive (as supplied) based on the total formulation in a standard-color masterbatch with up to 40 % pigment content.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Do not use with components that are sensitive to the presence of water (e.g. polyester) or in machinery that does not have adequate degassing vents.

Care Products and Polishes

Special Features and Benefits

HORDAMER PE 02 is compatible with all known polymer dispersions and plasticizers. The product provides good protection against heel marks (= black heel resistance), reduces dirt pick-up and shows good fill capacity. Blending HORDAMER PE 02 with polymers in a ratio of 3:1 (solid wax to solid polymer) particularly emphasizes the fill capacity and the dirt-repellent effect. Mixing at a ratio of 1:6 increases the water and alcohol resistance, scuff resistance, and black heel resistance.

Recommended Use

HORDAMER PE 02 is used in self-shine emulsions, wax cleaners and emulsion cleaners.

Recommended Levels

5-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wax additive is preferably added after blending the polymers with the plasticizers and water, however prior to the incorporation of surfactants while stirring.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.