



LOXIOI[®] GE 2063

Lubricant / Release Agent

Description

LOXIOI[®] GE 2063 is a co-stabilizing lubricant blend.

General Appearance

Light-yellowish
Available as powder

Specified Data

Parameter	Value	Test Method
Acid value (mg KOH/g)	0 - 3	DIN EN ISO 2114
Melting range (°C)	90 - 130	Q-P 1887
Ash (1000 °C, %)	38 - 42	DIN EN ISO 6245

Properties and Applications

LOXIOI[®] GE 2063 has a high external lubricating effect and is used to achieve higher output rates where the torsional moment of the machine requires a strong external lubricating effect. Due to its co-stabilizing properties LOXIOI[®] GE 2063 is only used in Sn-stabilized formulations.

LOXIOI[®] GE 2063 is mainly used for the manufacture of foamed rigid PVC extrudates as an external lubricant. To improve the flow properties, LOXIOI[®] GE 2063 can be combined with internal lubricants, such as LOXIOI[®] G 59. The product is not suitable for transparent applications.



Recommended Dosage

1.75 - 2.5 phr

Certifications

LOXIOL®, EDENOL® and EMEROX® products are compliant with many chemical regulations such as REACH as well as national chemical inventories depending upon the region. For questions regarding the registration status in your country, please contact your local sales or distribution partner.

Health and Safety Information

Please review our Safety Data Sheet for best practices when using this material.

Packaging Sizes

Bags, 25 kg

Big bags, 900 kg

Storage and Handling

The recommended storage for LOXIOL® GE 2063 is at room temperature. If stored in original sealed packaging, LOXIOL® GE 2063 should be stable for at least 24 months from the date of manufacture.

For more information, contact your nearest regional office.

Americas: gp.americas@emeryoleo.com

Europe: gp.europe@emeryoleo.com

Asia: gp.asia@emeryoleo.com

Disclaimer: The content in this document is provided on an "as is" and "as available" basis purely for informational purposes and, unless and to the extent specifically agreed otherwise for a sales transaction, does not constitute any warranty, whether express, implied or statutory, including but not limited to warranties or guarantees of merchantability, fitness or suitability for a particular purpose nor any representations of a binding nature. EMERY OLEOCHEMICALS EXPRESSLY DISCLAIMS ANY RESPONSIBILITY FOR THE SUITABILITY OF THE PRODUCTS FOR ANY SPECIFIC OR PARTICULAR PURPOSES INTENDED BY THE USER. Suggestions for the use and application of the products and guide formulations are for informational purposes only and you are advised to carry out any necessary steps to test the suitability of the products for your intended processes and purposes. You are solely responsible for compliance with all applicable laws and regulations in use of the products including any third party intellectual property rights and shall bear all liability or risk arising from use of the products. All indications marked with a TM or ® symbol are trademarks belonging to legal entities within the Emery Oleochemicals group of companies.