

NAN YA EPOXY RESIN

Data sheet No:901X75-1706E

NPSN-901X75

General:

NPSN-901X75 is a 75% N. V. solution of NPES-901 in Xylene used in anticorrosive paint.

NPSN-901X75 is cured with polyamide or polyamine hardeners, it provides good levels of chemical resistance and physical properties.


Chemical Composition:

Diglycidyl ether of Bisphenol-A (75%) + Xylene (25%)

Sale Specification & Typical Properties:

| | |
|--------------------------------|------------|
| Physical State | Liquid |
| Epoxy Equivalent Weight (g/eq) | 450~500 |
| Color (Gardner) | 1.0max |
| Viscosity (cps , at 25 °C) | 8000~15000 |
| N.V (%) | 74~76 |

Viscosity vs. Temperature Characteristics:



NAN YA EPOXY RESIN

Data sheet No:901X75-1706E

| |
|--------------------|
| NPSN-901X75 |
|--------------------|

Application:

Anticorrosive paint.

Storage properties:

At least 12 months in sealed containers at ambient temperature.

The resin should be stored in a dry place in its original closed packaging.

Handling precautions:

Product may cause skin and eye irritation. In cases of skin contact wash immediately with soap and water. For eyes, flush with plenty of water for 15 minutes and seek medical attention immediately.