

Data Sheet Issue 01/2021

RHEOBYK-7411 ES

Liquid rheology additive for low-polarity solvent-borne and solvent-free coating systems and cleaning products to generate highly thixotropic flow behavior and to improve the anti-sagging and anti-settling properties.

Product Data

Composition

Solution of a modified urea

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Active substance:25 %Density (20 °C):1.07 g/mlSolvents:Amide esterFlash point:146 °C

Storage and Transportation

Moisture sensitive. Store dry. Minor cloudiness of the material that occurs during storage has no influence on the rheological effectivity. The specified storage stability upon dispatch applies when the product is handled correctly and stored in unopened original containers.

Applications

Coatings Industry

Special Features and Benefits

After being stirred into the coating system, the additive generates a three-dimensional network structure. The resulting thixotropic flow behavior is highly suited for preventing sedimentation and increasing the anti-sagging properties without impairing leveling. As a result of associated interaction of RHEOBYK-7411 ES with the used binder, the rheological effect is also significantly dependent upon the type and quantity of the binder.

Recommended Use

The additive is recommended for low-polarity systems. RHEOBYK-7410 ET is better suited for medium-polarity systems. We recommend RHEOBYK-7420 ES for high-polarity and aqueous systems.

Recommended Levels

0.2-1 % additive (as supplied) based on the total formulation to prevent settling. 0.5-2 % additive (as supplied) based on the total formulation to prevent sagging.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Data Sheet Issue 01/2021

Incorporation and Processing Instructions

The additive should be added to the coating whilst stirring using moderate shear forces to ensure a homogeneous and quick distribution. It is not necessary to specifically control the temperature. The additive can be added to the millbase and is also suitable for adjusting the viscosity afterwards by incorporating it as a post-additive.

Special Note

If used with driers (siccatives), discoloration may occur due to the formation of metal complexes. The rheological effectiveness should then be tested.

Detergents, Cleaning and Care Products

Special Features and Benefits

After being incorporated into the system, the additive generates a three-dimensional network structure. The resulting thixotropic flow behavior is ideal for preventing particles (e.g. encapsulated fragrances) from settling, without negatively impacting the residual emptying of the container. Cleaning products with RHEOBYK-7411 ES are easy to use and can be applied by spraying. The use of the additive improves adhesion to vertical surfaces, which improves the cleaning action as a result of the longer exposure time. The additive is liquid and therefore easy to handle. The transparency of the detergents and cleaning products is preserved.

Recommended Use

RHEOBYK-7411 ES is used as a rheology additive to improve the anti-sagging and anti-settling properties in detergents and cleaning products based on low-polarity solvents. It can also be used in liquid, nonionic surfactants (alcohol ethoxylates and propoxylates of low polarity).

| Industrial cleaners (non-polar solvents) | |
|--|--|
| Non-aqueous liquid detergents | |
| especially recommended recommended | |

Recommended Levels

1.0-3.0% additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added whilst stirring using moderate shear forces to ensure a rapid, homogeneous distribution. It is not necessary to specifically control the temperature. The additive is also suitable for subsequently adjusting the viscosity by incorporating it as a post-additive. The additive is recommended for low-polarity systems.

RHEOBYK-7411 ES

Data Sheet Issue 01/2021

RHEOBYK-7411 ES

Data Sheet Issue 01/2021



Google play

BYK-Chemie GmbH P.O. Box 10 02 45 46462 Wesel Germany Tel +49 281 670-0 Fax +49 281 65735

info@byk.com www.byk.com ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERBYK®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, POLYAD®, PRIEX®, PURE THK®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSOR®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.