

## Product Information



Omya International AG  
P.O. Box  
CH-4665 Oftringen

+41 62 789 29 29  
+41 62 789 20 77

www.omya.com

# SNOWHITE 12-40 - PT

PRODUCTION SITE:	<b>PERTH</b> , Canada (certified ISO 9001, ISO 14001, ISO 45001)									
SHORT DESCRIPTION OF THE PRODUCT:	A bright white, dry screen-separated grade									
CHEMICAL ANALYSIS:	<table><tr><td>CaCO<sub>3</sub></td><td>94</td><td>%</td></tr><tr><td>MgCO<sub>3</sub></td><td>2</td><td>%</td></tr></table>	CaCO <sub>3</sub>	94	%	MgCO <sub>3</sub>	2	%			
CaCO <sub>3</sub>	94	%								
MgCO <sub>3</sub>	2	%								
SPECIFIC PRODUCT DATA:	<p>Fineness:</p> <ul style="list-style-type: none"><li>Residue on a 325 mesh sieve (Omya GLS 021) 100 %</li><li>Residue on a 200 mesh sieve (Omya GLS 021) 100 %</li><li>Residue on a 40 mesh sieve (Omya GLS 021) 80 %</li><li>Residue on a 12 mesh sieve (Omya GLS 021) 0 %</li></ul> <p>Optical Properties:</p> <ul style="list-style-type: none"><li>Brightness Ry (Omya GLS 035) 85 %</li></ul> <p>Moisture ex works (Omya GLS 006) 0.02 %</p>									
GENERAL PRODUCT DATA:	<table><tr><td>Loose Bulk density (Omya GLS 001)</td><td>1.67</td><td>g/ml</td></tr><tr><td>Tapped Bulk density (Omya GLS 002)</td><td>1.74</td><td>g/ml</td></tr><tr><td>Specific Gravity (ISO 787-10)</td><td>2.71</td><td></td></tr></table>	Loose Bulk density (Omya GLS 001)	1.67	g/ml	Tapped Bulk density (Omya GLS 002)	1.74	g/ml	Specific Gravity (ISO 787-10)	2.71	
Loose Bulk density (Omya GLS 001)	1.67	g/ml								
Tapped Bulk density (Omya GLS 002)	1.74	g/ml								
Specific Gravity (ISO 787-10)	2.71									
MAIN APPLICATIONS :	Concrete matrix and mortar sand ASTM golf bunker sand.									
REGULATORY APPROVAL :	This product may be used as an indirect food additive in food packaging applications un-der 21 CFR (FDA) 174.5, 175.300, and 178.3297. It does not qualify as a substance permitted for direct addition to human food.									
STANDARD PACKAGING:	Bulk Bag - 50lbs Big Bags									

The information contained in this Product Information Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Omya believes to be reliable, however Omya makes no representation or warranty as to the completeness or accuracy thereof and Omya assumes no liability resulting from its use or for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.

edition: 21.09.2023  
version: 2