



Technical Data Sheet

Xperse® 401

Dispersion of Zano® 10 Plus and TiO₂ (alumina and stearic acid coated) in caprylic/capric triglyceride

General Characters

Appearance Off-white slurry

Product specifications	Specifications	Method
Residue of ignition	52 - 58 %	15 min 800°C
Zinc Oxide content	25.5 - 29.5 %	Mass balance calculations
Titanium dioxide content	20 - 24 %	Mass balance calculations

INCI constituents (Composition)	Nominal content
Zinc oxide	29 w%
Titanium dioxide (nano)	23 w%
Caprylic/capric triglyceride	35 w%
Polyhydroxystearic acid	5 w%
Alumina	3.5 w%
Stearic acid	3.5 w%
Triethoxycaprylsilane	1 w%

Product specifications for Zano® 10 Plus (*)	Specifications	Method
Lead	≤ 0.0010 %	ICP-AES
Cadmium	≤ 0.0005 %	ICP-AES
Iron	≤ 0.0050 %	ICP-AES
Thallium	≤ 0.0005 %	ICP-AES
Arsenic	≤ 0.0002 %	ICP-AES

(*) Prior to surface treatment

Packaging: 25 kg in plastic pail

SPEC-5060 Revision: 5 Date: 14-Sep-2022