



## **Technical Data Sheet** Zano® 20

Zano® 20 is manufactured and tested in compliance with GMP Part II / ICH Q7 requirements. Testing is done using EP/USP analytical methods or validated in-house analytical methods and is compliant to below mentioned specifications.

## General characters (EP) for Zano® 20

Appearance: soft, white or faintly yellowish-white, amorphous powder, free from gritty particles. Solubility: practically insoluble in water and in ethanol (96 per cent). It dissolves in dilute mineral acids.

## Zinc oxide EP/USP product specifications for Zano® 20

	Specification	Method
Identification A, B	PASS	EP/USP
Zinc Oxide	99,0 – 100,5 %	EP/USP
Lead	≤0,0010 %	ICP-AES
Cadmium	≤0,0005 %	ICP-AES
Iron	≤0,0050 %	ICP-AES
Arsenic	≤0,0002 %	ICP-AES
Thallium	≤0,0005 %	ICP-AES
Iron and other heavy metals	PASS	USP
Alkalinity	PASS	EP/USP
Loss on Ignition	≤1,0 %	EP/USP
Carbonates and color of solution	PASS	USP
Carbonates and substances insoluble in acids	PASS	EP

## Additional specifications for Zano® 20

	Specification	Method
Aluminium	≤0,0020 %	ICP-AES
Specific surface area (after production)	$\geq$ 28,0 m <sup>2</sup> /g	BET

12.5 -20 kg bags in cardboard box Packaging:





SPEC-0654