



Technical Data Sheet Zano[®] D

Zano[®] D is manufactured and tested in compliance with GMP Part II / ICH Q7 requirements. Testing is done using EP/USP analytical methods or validated in-house analytical methods and is compliant to below mentioned specifications.

Zano[®] D is not suitable for UV applications.

General characters (EP) for Zano® D

Appearance: soft, white or faintly yellowish-white, amorphous powder, free from gritty particles. *Solubility*: practically insoluble in water and in ethanol (96 per cent). It dissolves in dilute mineral acids.

Zinc oxide EP/USP product specifications for Zano® D

	Specification	Method
Identification A, B	PASS	EP/USP
Zinc Oxide	99,0 – 100,5 %	EP/USP
Lead	≤0,0010 %	ICP-AES
Cadmium	≤0,0005 %	ICP-AES
Iron	≤0 <i>,</i> 0050 %	ICP-AES
Arsenic	≤0,0002 %	ICP-AES
Thallium	≤0,0005 %	ICP-AES
Iron and other heavy metals	PASS	USP
Alkalinity	PASS	EP/USP
Loss on Ignition	≤1,0 %	EP/USP
Carbonates and color of solution	PASS	USP
Carbonates and substances insoluble in acids	PASS	EP

Additional specifications for Zano® D

	••••••••••
Aluminium	≤0 <i>,</i> 0020 %
Specific surface area (after production)	≥ 33,0 m²/g

 Specification
 Method

 ≤0,0020 %
 ICP-AES

 ≥ 33,0 m²/g
 BET

Packaging:

20 kg bags in cardboard box



SPEC-5077 Revision : 2 Date : 30-Sep-2022

information@evercare-zano.com www.evercare-zano.com