Innovative Chemistry for Lubricants

Technical Data Sheet

FUNCTIONAL MH-2000

Methacrylate-based Viscosity Index Improver for Hydraulic Fluid and Multi-grade Gear Oil

APPLICATION:

FUNCTIONAL MH-2000 is a liquid-form polyalkylmethacrylate viscosity modifier that offers high thickening efficiency with excellent shear stability. **FUNCTIONAL MH-2000** has been specifically formulated to provide additional VI improvement, demulsibility, and pour point depressancy. The high shear stability and low temperature performance also makes **FUNCTIONAL MH-2000** attractive in multi-grade gear oil formulations.

COMPOSITION:

FUNCTIONAL MH-2000 is a blend of polyalkylmethacrylates and highly refined mineral oil.

Typical Properties			
Lbs per Gallon (ASTM D 1475)	7.8		
Specific Gravity	0.93		
Kinematic Viscosity (ASTM D 445)	1100 at 100 °C		
Thickening Efficiency (10% in ISO 32)	9.2 cSt at 100 °C		
PSSI (5% in 150N, ASTM D 6278)	1%		
Sonic Shear (10wt% in 150N)	12%		
KRL (20hr)	35%		
Flash Point (ASTM D 92)	>150°C		
Color (ASTM D 1500)	< 1.0		

TREATMENT LEVEL:

Typical treatment level for methacrylate-based viscosity modifiers ranges from 5 to 10% for hydraulic fluids and 5% to 20% for gear oils. 10% **FUNCTIONAL MH-2000** will increase an ISO 32 oil to ISO 46.

wt% Treat	100N Oil (ISO 22)	150N Oil (ISO 32)	200N Oil (ISO 46)	350N Oil (ISO 68)
0%	3.9	5.4	6.5	8.3
5%	5.2	6.7	8.1	10.5
10%	6.9	8.8	10.2	13.2
20%	11.5	15.4	16.0	18.0

FUNCTIONAL MH-2000 Treat Level vs. Viscosity @ 100°C

HANDLING:

FUNCTIONAL MH-2000 should be warmed to about 50°C (120°F) to facilitate pumping and handling. The base oil should be heated to 60-80°C (140-180°F) during blending to allow for good mixing. Mixing time will vary with equipment but is typically at least one hour. Safe handling precautions are the same as those to be taken with base oil; see the current Safety Data Sheet.

This Technical Data Sheet and the Safety Data Sheet contain information believed to be accurate and reliable. No warranty is made, however, to information beyond the control of FUNCTIONAL PRODUCTS INC. The engineering and management personnel of the user are responsible for determining the suitability of this or any product for any specific application, and this information is offered to them for that purpose.

FUNCTIONAL PRODUCTS INC.

Innovative Chemistry for Lubricants

Technical Data Sheet

FUNCTIONAL MH-2000 Treat Levels:*

To obtain specific viscosity grades from a 100N (ISO 22) base oil:

	Treat (wt%)	40°C Viscosity	100°C Viscosity	VI
100N (ISO 22)	0.0%	19.4 cSt	3.9 cSt	92
150N (ISO 32)	9.9%	32.6 cSt	6.9 cSt	179

To obtain specific viscosity grades from a 150N (ISO 32) base oil:

	Treat (wt%)	40°C Viscosity	100°C Viscosity	VI
150N (ISO 32)	0.0%	30.6 cSt	5.4 cSt	117
200N (ISO 46)	9.9%	47.5 cSt	8.8 cSt	167

* These levels are suggested. Intermediate 40°C viscosities may be achieved by varying wt% linearly.

Actual treat levels will vary due to base oil composition and other additives.

The oils featured on this page are separate from the ISO 32 oil for 10wt% thickening efficiency on page 1.

This Technical Data Sheet and the Safety Data Sheet contain information believed to be accurate and reliable. No warranty is made, however, to information beyond the control of FUNCTIONAL PRODUCTS INC. The engineering and management personnel of the user are responsible for determining the suitability of this or any product for any specific application, and this information is offered to them for that purpose.