

## DESCRIPTION

**Aegis® H100MP** is a lubricated and nucleated medium viscosity nylon 6 extrusion grade homopolymer for cast or blown film applications. It conforms to FDA requirements of 21 CFR 177.1500 as well as EU Directive 2011/10/EC. Aegis® H100MP homopolymer possesses the combination of strength, toughness and thermoforming properties associated with nylon 6 as well as excellent heat, chemical and abrasion resistance.

## PHYSICAL AND CHEMICAL PROPERTIES

GENERAL PROPERTIES	TEST METHOD	UNIT	VALUE
<b>Parameter</b>			
Viscosity, FAV	ASTM D-789		100
RV @ 96% Sulfuric Acid			3.35
Extractable Content	SOP-702-307	%	Max. 0.8
Density	ASTM D-792	g/cm <sup>3</sup>	1.13
Melt Flow Rate, 235°C/1.0 kg (455°F/1.0 kg)	ASTM D-1238	g/10 min	2.6
<b>Moisture</b>			
Moisture Content	ASTM D-6869	%	Max. 0.08
Moisture (24 Hour)	ASTM D-570	%	1.6
Moisture (50% RH)	ASTM D-570	%	2.7
Moisture (Saturation)	ASTM D-570	%	9.5
<b>Thermal</b>			
Melting Point	ASTM D-3418	°C (°F)	220°C (428°F)

FILM PROPERTIES	TEST METHOD	UNIT	VALUE
<b>Gas Barrier @ 23°C (73°F)/0% RH</b>			
Oxygen Permeability	ASTM D-3985	cc/m <sup>2</sup> /day	40.3
Water Vapor Permeability @ 38°C (100°F)/100% RH	F-1249	gm/m <sup>2</sup> /day	992
Nitrogen Permeability		cc/m <sup>2</sup> /day	14.0
Carbon Dioxide Permeability		cc/m <sup>2</sup> /day	72.8

FILM PROPERTIES (CONTINUED)	TEST METHOD	UNIT	VALUE (MD)*	VALUE (TD)*
<b>Mechanical</b>				
Tensile Modulus, 23°C (73°F)	ASTM D-882	MPa	700	590
Tensile Yield, 23°C (73°F)	ASTM D-882	MPa	30	30
Tensile Strength, 23°C (73°F)	ASTM D-882	MPa	90	80
Elongation, 23°C (73°F)	ASTM D-882	%	340	340
Graves Tear, 23°C (73°F)	ASTM D-1004	N	2140	2070
Elmendorf Tear Strength, 23°C (73°F)	ASTM D-1992	N	880	950
Puncture Strength, 23°C (73°F)	ASTM D-5478	grams	960	-
Puncture Index, 23°C (73°F)	ASTM D-5478	gm/mil	470	-

\*Note: MD = Machine Direction and TD = Traverse Direction. Test samples obtained from 2-mil thick unoriented cast film.

MOLDED PROPERTIES	TEST METHOD	UNIT	VALUE (MD)*
<b>Mechanical</b>			
Tensile Modulus, 23°C (73°F)	ASTM D-882	MPa	3,240
Tensile Strength, 23°C (73°F)	ASTM D-882	MPa	80
Yield Elongation, 23°C (73°F)	ASTM D-882	%	3.8
Flexural Modulus, 23°C (73°F)	ASTM D-790	MPa	2,650
Flexural Strength, 23°C (73°F)	ASTM D-790	MPa	110
Notched Izod, 23°C (73°F)	ASTM D-256	J/m	60
Heat Deflection Temperature, 23°C (73°F)	ASTM D-648	°C (°F)	61 (142)

Processing conditions for test specimens: melt temperature = 240°C (464°F); mold temperature = 80°C (176°F).

## PROCESSING GUIDELINES

### Material Handling

Aegis® H100MP homopolymer is supplied in sealed containers and drying prior to processing is not required. However, high moisture is the primary cause of processing problems. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet on [AdvanSix.com](https://www.advanSix.com). Alternatively, please contact your AdvanSix representative.

## EXTRUSION GUIDELINES

### Melt Viscosity vs. Temperature

Melt Temperature: 220°C (428°F)

Melt Temperature Range: 232°C (450°F) to 271°C (520°F).

Two key factors affect the melt viscosity (stiffness or fluidity of the melt):

1. The molecular weight (MW) of the resin: Higher MW resins will have a higher melt viscosity than lower MW resins.
2. Temperature of the melt for any given MW resin: Higher process temperatures will provide a more fluid melt viscosity than lower process temperatures.

### Typical Barrel Profile for Cast Films

Barrel: 230–260°C (446–500°F)

Adapter: 260–266°C (500–510°F)

Die: 260°C (500°F)

Process Melt Temperature: 260–270°C (500–518°F)

### Screw Parameters

Metering Section: 40%

Transition Section: 3 to 4 flights

Feed Section: Balance of screw length

Compression Ratio: 3.5:1 to 4.0:1

L/D Ratio: 24:1

### Typical Barrel Profile for Tubular (Blown) Films

Barrel: 246–254°C (474–490°F)

Adapter: 260°C (500°F)

Die: 254°C (490°F)

Process Melt Temperature: 254–260°C (490–500°F)

### Metering Section Flight Depth

SCREW DIAMETER	RECOMMENDED DEPTH
1"	0.055"
1.5"	0.060"
2"	0.070"
2.5"	0.080"
3.5"	0.100"
4.5"	0.115"
6"	0.135"

## NOTE

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.

The values in this data sheet are for natural color resins only. Colorants or other additives may alter some or all of these properties. The data listed here fall within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design.

Although AdvanSix Inc. believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute representation or warranty of AdvanSix Inc., either expressed or implied. A number of factors may affect the performance of products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided in this document does not relieve the user from the responsibility of carrying out independent tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.

Aegis® is a registered trademark of AdvanSix Inc.  
©2024 AdvanSix Inc. All rights reserved.

## CONTACT ADVANSIX

Contact AdvanSix to learn more about the benefits of our Nylon Resins.

**ADVANSIX.COM**  
1-844-890-8949 (TOLL FREE, U.S./CAN.)  
+1-973-526-1800 (INTERNATIONAL)

## ADVANSIX HEADQUARTERS

300 Kimball Drive, Suite 101  
Parsippany, NJ 07054

